

# Technical Data Sheet

## Pigment Blue 60



FINELAND CHEM  
泛成化工

### General Information

Color Index:	Pigment Blue 60(C.I. 69800)
Product Code:	3660
CAS NO.:	81-77-6
EC No.:	201-375-5
Chemical Formula:	C <sub>28</sub> H <sub>14</sub> N <sub>2</sub> O <sub>4</sub>

### Physical Properties

Residue on sieve 325mesh(ppm)	≤ 600
Oil Absorption (g/100g):	40-65
Water Soluble Matter (%):	≤ 1.5
Moisture Content(%):	≤ 1.5
PH Value:	6-9
Physical Appearance	Same to Std.

### Fastness Properties

Heat Resistance (°C):	300	Alkali Resistance (1~5):	5
Light Resistance (Full Shade, 1~8):	8	Migration Resistance(1~5)	5
Light (Reduced tinting, 1~8)	7	Ethyl Acetate (1~5)	5
Weather Resistance (1~5):	5	Ethanol (1~5)	5
Acid Resistance (1~5):	5	MEK (1~5)	5

### Application & Performance

Recommended for polyester fiber (PET/terylene), PA fiber (chinson), polypropylene fiber(PP fiber), automotive coating, PP HDPE PVC PS PET PA Plastic and engineering plastics.Reddish blue.

### Note

\*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue: Sept 1<sup>st</sup>, 2024

TDS Version: 2.1