


## Naphthol Carmine FBB

**Color Type** Quinacridone

**Color Index No.** P.R.146

**CAS NO.** 5280-68-2

**Structure:**



**Description :**

- Recommend for Paint, Latex and Architectural Coatings, Textile printing, and Printing ink, good in different solvents, only workable for hard PVC

**Physical Properties :**

Items	Data
Density (g/cm <sup>3</sup> )	1.35-1.40
Specific Surface Area ( m <sup>2</sup> /g )	36-40
Oil Absorption (g/100g)	65-70
PH Value	5.5
Bulk Density (lb/gal)	11.2-11.6

Fastness Properties	Data
Heat Resistance ( °C )	200
Light Resistance ( Full Shade, 1~8 )	5-7
Weather Resistance (1~5)	4-5
Acid Resistance (1~5)	4
Alkali Resistance (1~5)	4
Alcohol Resistance (1~5)	4
Ester Resistance	4
Benzene Resistance	4
Ketone Resistance	4

**Applications :**

Inks	Offset Ink	◎
	Gravure Ink	●
	UV Ink	◎
	Solvent borne	●
	Water borne	◎
Paints	Decorate paint	●
	Textile printing	●
	Industrial	●
	Wood painting	●
Plastic	Hard PVC	●

Remark: ●High Recommendation;

◎Recommendation; - Limit Suitability

**Storage conditions :**

Should be sealed for avoiding light and moisture.

**Package :**

25KG/ Kraft Bag

\*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

**Hangzhou Fancheng Chemical Co.,Ltd**

Add: No. 37 Jinyi Road, Xiaoshan, Hangzhou, China

Tel: +86-571-83531793

<http://www.finelandpigment.com/>