


Anthraquinoid Red

Color Type Anthraquinones
Color Index No. P.R. 177
CAS NO. 4051-63-2
Structure:



Description :

- Recommend for Paint, original pulp coloring and polyolefin and PVC coloring; And automotive paint primers and repair paints; Also suitable for the coating of various resin films and the coloring of special printing ink for coinage.

Physical Properties :

Items	Data
Density (g/cm ³)	1.45-1.53
Specific Surface Area (m ² /g)	65-106
Oil Absorption (g/100g)	55-62
PH Value	7.0-7.2
Bulk Destity (lb/gal)	12.1-12.7

Fastness Properties	Data
Heat Resistance (°C)	300
Light Resistance (Full Shade, 1~8)	4-5
Weather Resistance (1~5)	4
Acid Resistance (1~5)	5
Alkali Resistance (1~5)	5
Ester Resistance	5

Hangzhou Fancheng Chemical Co.,Ltd
Add: No. 37 Jinyi Road, Xiaoshan, Hangzhou, China
Tel: +86-571-83531793
<http://www.finelandpigment.com/>

Applications :

Inks	Offset Ink	◎
	UV Ink	◎
Paints	Automotive OEM	●
	Car Refinish	●
	Industrial	◎
	Powder Coating	◎
Plastic	PVC	●
	PO	◎
	HDPE	●

Remark: ●High Recommendation;
◎Recommendation; - Limit Suitability

Storage conditions :

Should be sealed for avoiding light and moisture.

Package :

25KG/ Kraft Bag

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.