Technical Data Sheet



Pigment Orange 34

General Information

| Color Index | Pigment orange 34 (C.I. 21115) |
|------------------|--------------------------------|
| Product Code | 6234Y+1 |
| CAS NO. | 15793-73-4 |
| EC No. | 239-898-6 |
| Chemical Formula | $C_{34}H_{28}CI_2N_8O_2$ |

Physical Properties

| Density (g/cm³) | 1.35-1.45 |
|--|-----------|
| Specific Surface Area(m ² /g) | 35-75 |
| Oil Absorption (g/100g) | 43-79 |
| PH Value | 4.8-6.5 |
| Bulk Density (lb/gal) | 11.0-11.6 |
| Total impurities(ppm) | ≦600 |

Fastness Properties

| | Heat Resistance (°C) | 200 | Alkali Res |
|--|------------------------------------|-----|------------|
| | Light Resistance (Full Shade, 1-8) | 5-6 | Migration |
| | Light (Reduced tinting, 1-8) | 4-5 | Ethyl Ace |
| | Weather Resistance (1-5) | 5 | Ethanol (|
| | Acid Resistance (1-5) | 4 | MEK (1-5 |

| Alkali Resistance (1-5) | 4 |
|---------------------------|---|
| Migration Resistance(1-5) | 4 |
| Ethyl Acetate (1-5) | 4 |
| Ethanol (1-5) | 5 |
| MEK (1-5) | 4 |

Application & Performance

Recommended for paint and coating, with yellowish color shade and good Light Resistance & Weather Resistance. Color strentgh a little lower than 6234Y.

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue Sep. 1st, 2024

TDS Version 2.1