# **Technical Data Sheet**



# **Pigment Red 21**

#### **General Information**

Color Index	Pigment Red 21 (C.I. 12300)
Product Code	6521
CAS NO.	3789-75-1
EC No.	229-096-4
Chemical Formula	$C_{23}H_{17}N_3O_2$

## **Physical Properties**

Density (g/cm³)	1.10-1.45
Specific Surface Area(m <sup>2</sup> /g)	33-63
Oil Absorption (g/100g)	35-50
PH Value	6.5-8.5
Bulk Density (lb/gal)	12.0-13.5
Total impurities(ppm)	≦600

## **Fastness Properties**

Heat Resistance (°C)	160
Light Resistance (Full Shade, 1-8)	5-6
Light (Reduced tinting, 1-8)	4-5
Weather Resistance (1-5)	5
Acid Resistance (1-5)	4

Alkali Resistance (1-5)	4
Migration Resistance(1-5)	5
Ethyl Acetate (1-5)	4
Ethanol (1-5)	5
MEK (1-5)	4

# **Application & Performance**

Recommended for paint, widely used in red enamel, latex paint, watercolor and oil paint pigments, cultural and educational tools, and fabric printing and dyeing. It is bright yellow light red.

#### Note

\*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue Sep 1<sup>st</sup> , 2024 TDS Version 2.1

Hangzhou Fancheng Chemical Co.,Ltd.

Add NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China.

Tel +86-571-83531793

Web: www.finelandchem.com