# **Technical Data Sheet**



### Pigment Red 48:2

#### **General Information**

Color Index	Pigment Red 48:2 (C.I. 15865:2)
Product Code	3582 2BP-1
CAS NO.	7023-61-2
EC No.	230-303-5
Chemical Formula	C <sub>18</sub> H <sub>11</sub> CLN <sub>2</sub> O <sub>6</sub> SCa

## **Physical Properties**

Density (g/cm³)	1.5-1.8
Specific Surface Area(m <sup>2</sup> /g)	53-100
Oil Absorption (g/100g)	35-67
PH Value	6-9
Bulk Density (lb/gal)	12.5-15.5
Total impurities(ppm)	≦600

#### **Fastness Properties**

Heat Resistance (°C)	240-
	260
Light Resistance (Full Shade, 1-8)	5-6
Light (Reduced tinting, 1-8)	4-5
Weather Resistance (1-5)	3-4
Acid Resistance (1-5)	4-5

Alkali Resistance (1-5)	3
Migration Resistance (1-5)	4-5
Ethyl Acetate (1-5)	4
Ethanol (1-5)	4
MEK (1-5)	3

### **Application & Performance**

Bluish shade grade with high heat resistance, excellent dispersion and superb migration resistance. It's mainly used for plastics like PVC, PP, PE etc. and PU Foam.

#### Note

\*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue: Sep., 1st 2024

TDS Version: 2.1

Tel: +86-571-83531793 Web: www.finelandchem.com