

Technical Data Sheet

Pigment Red 49:1



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Red 49:1 (C.I. 15630:1)
Product Code	W6591C-1
CAS NO.	1103-38-4
EC No.	214-160-6
Chemical Formula	C ₄₀ H ₂₆ N ₄ O ₈ S ₂ Ba

Physical Properties

Density (g/cm ³)	1.48-1.90
Specific Surface Area(m ² /g)	32-67
Oil Absorption (g/100g)	40-65
PH Value	7-9
Bulk Density (lb/gal)	12.3-15.8
Total impurities(ppm)	≦ 600

Fastness Properties

Heat Resistance (°C)	160	Alkali Resistance (1-5)	4
Light Resistance (Full Shade, 1-8)	4~5	Bleeding Resistance(1-5)	-
Light (Reduced tinting, 1-8)	4	Ethyl Acetate (1-5)	3
Weather Resistance (1-5)	3~4	Ethanol (1-5)	4
Acid Resistance (1-5)	3	MEK (1-5)	3

Application & Performance

Recommended for ink(water based flexo/gravure inks).

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue Sep. 1st, 2024

TDS Version 2.1