Technical Data Sheet



Pigment Red 81

General Information

| Color Index | Pigment Red 81 (C.I. 45160) | | |
|------------------|-----------------------------|--|--|
| Product Code | 6581C | | |
| CAS NO. | 12224-98-5 | | |
| EC No. | 235-424-7 | | |
| Chemical Formula | $C_{28}H_{31}N_2O_3$ | | |

Physical Properties

| Density (g/cm ³) | 1.55-1.85 |
|--|-----------|
| Specific Surface Area(m ² /g) | 25-60 |
| Oil Absorption (g/100g) | 45-50 |
| PH Value | 6.5-7.5 |
| Bulk Density (lb/gal) | 10.4-12.5 |
| Total impurities(ppm) | ≦600 |

Fastness Properties

| Heat Resistance (°C) | 160 | Alkali Resistance (1-5) | 4 |
|------------------------------------|-----|---------------------------|---|
| Light Resistance (Full Shade, 1-8) | 7-8 | Migration Resistance(1-5) | 5 |
| Light (Reduced tinting, 1-8) | 6-7 | Ethyl Acetate (1-5) | 3 |
| Weather Resistance (1-5) | 4 | Ethanol (1-5) | 4 |
| Acid Resistance (1-5) | 4 | MEK (1-5) | 2 |

Application & Performance

Recommended for water-based Ink, It's a bright bluish red lake pigment with strong color strength.

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

> Date of issue Sep 1st , 2024 TDS Version 2.1

Hangzhou Fancheng Chemical Co.,Ltd. Add NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China. Tel +86-571-83531793 Web: www.finelandchem.com Fineland Chem Co., Ltd. Add Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkog, Kl, HK