Technical Data Sheet



Pigment Violet 19

General Information

Color Index	Pigment Violet 19 (C.I. 73900)		
Product Code	3019B		
CAS NO.	1047-16-1		
EC No.	213-879-2		
Chemical Formula	$C_{20}H_{12}N_2O_2$		

Physical Properties

Density (g/cm ³)	1.50-1.80
Specific Surface Area(m ² /g)	22-85
Oil Absorption (g/100g)	40-70
PH Value	6.5-9.0
Bulk Density (lb/gal)	12.6-14.8
Total impurities(ppm)	≦600

Fastness Properties

Heat Resistance (°C)	300	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	7-8	Bleeding Resistance(1-5)	5
Light (Reduced tinting, 1-8)	6-7	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	5	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	5

Application & Performance

Recommended for coating(OEM, coil, powder), plastic(PVC, PUR, PP, HDPE), ink(metal decorative).

 β -Modification, reddish violet shade.

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

> Date of issue Sep. 1st , 2024 TDS Version 2.1

Hangzhou Fancheng Chemical Co.,Ltd. Add NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China. Tel: +86-571-83531793 Web: www.finelandchem.com Fineland Chem Co., Ltd. Add Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkog, Kl, HK