# **Technical Data Sheet**



## **Pigment Violet 3**

|       |      |      |      | •   |
|-------|------|------|------|-----|
| Gen   | oral | Into | rmat | ion |
| 7-7-4 |      |      |      |     |

| Color Index      | Pigment Violet 3 (C.I. 42535)                  |
|------------------|--|
| Product Code     | W6003B   |
| CAS NO.          | 1325-82-2                                      |
| EC No.           | 273-548-3                                      |
| Chemical Formula | C <sub>24</sub> H <sub>27</sub> N <sub>3</sub> |

## **Physical Properties**

| Density (g/cm³):                          | 2.1-2.3   |
|---|-----------|
| Specific Surface Area(m <sup>2</sup> /g): | 3.6-4.5   |
| Oil Absorption (g/100g):                  | 40-80     |
| PH Value:                                 | 6.5-8.5   |
| Bulk Density (lb/gal):                    | 17.9-19.1 |
| Total impurities(ppm)                     | ≦600      |

### **Fastness Properties**

| Heat Resistance (°C)               | 160 |
|------------------------------------|-----|
| Light Resistance (Full Shade, 1-8) | 6-7 |
| Light (Reduced tinting, 1-8)       | 5-6 |
| Weather Resistance (1-5)           | 4   |
| Acid Resistance (1-5)              | 4   |

| Alkali Resistance (1-5)   | 3 |
|---------------------------|---|
| Migration Resistance(1-5) | 4 |
| Ethyl Acetate (1-5)       | 3 |
| Ethanol (1-5)             | 4 |
| MEK (1-5)                 | 3 |

### **Application & Performance**

Recommended for water based ink. Bluish violet.

#### Note

\*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue: Sept 1st, 2024

TDS Version: 2.1