# **Technical Data Sheet**



## **Pigment Yellow 12**

#### **General Information**

Color Index	Pigment Yellow 12 (C.I. 21090)
Product Code	3176R
CAS NO.	6358-85-6
EC No.	228-787-8
Chemical Formula	C <sub>32</sub> H <sub>26</sub> Cl <sub>2</sub> N <sub>6</sub> O <sub>4</sub>

#### **Physical Properties**

Density (g/cm <sup>3</sup> )	1.35-1.55
Specific Surface Area(m <sup>2</sup> /g)	35-65
Oil Absorption (g/100g)	25-70
PH Value	5.0-8.5
Bulk Density (lb/gal)	9.3-13.6
Total impurities(ppm)	≦600

#### **Fastness Properties**

Heat Resistance (°C)	160	Alkali R
Light Resistance (Full Shade, 1-8)	2-3	Migrati
Light (Reduced tinting, 1-8)	1-2	Ethyl Ad
Weather Resistance (1-5)	4	Ethanol
Acid Resistance (1-5)	4	MEK (1-

Alkali Resistance (1-5)	4
Migration Resistance(1-5)	3
Ethyl Acetate (1-5)	3
Ethanol (1-5)	4
MEK (1-5)	2

### **Application & Performance**

Recommended for plastic(PVC, PE, PP, PS, rubber), higher color strength than 3176C-3 with good dispersions.

#### Note

\*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

> Date of issue Sep 1<sup>st</sup> , 2024 TDS Version 2.1

Hangzhou Fancheng Chemical Co.,Ltd. Add NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China. Tel +86-571-83531793 Web: www.finelandchem.com Fineland Chem Co., Ltd. Add Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkog, Kl, HK