# **Technical Data Sheet**



# Pigment Yellow 12

### **General Information**

Color Index	Pigment Yellow 12 (C.I. 21090)		
Product Code	H3176G-1		
CAS NO.	6358-85-6		
EC No.	228-787-8		
Chemical Formula	$C_{32}H_{26}CI_2N_6O_4$		

# **Physical Properties**

Density (g/cm <sup>3</sup> )	1.35-1.55
Specific Surface Area(m <sup>2</sup> /g)	38-75
Oil Absorption (g/100g)	24-67
PH Value	5.0-8.5
Bulk Density (lb/gal)	9.3-13.6
Total impurities(ppm)	≦600

#### **Fastness Properties**

Heat Resistance (°C)	160	Alkali Resistance (1-5)	4
Light Resistance (Full Shade, 1-8)	2-3	Migration Resistance(1-5)	3
Light (Reduced tinting, 1-8)	1-2	Ethyl Acetate (1-5)	3
Weather Resistance (1-5)	4	Ethanol (1-5)	4
Acid Resistance (1-5)	4	MEK (1-5)	2

## **Application & Performance**

Recommended for water-based application, high color strength, but lower than H3176G, mostly for water-based Ink.

#### Note

\*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

> Date of issue Sep 1<sup>st</sup> , 2024 TDS Version 2.1

Hangzhou Fancheng Chemical Co.,Ltd. Add NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China. Tel +86-571-83531793 Web: www.finelandchem.com **Fineland Chem Co., Ltd.** Add Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkog, KI, HK