Technical Data Sheet



Pigment Yellow 12

Gen	eral	Int	orm	ation	

Color Index	Pigment Yellow 12 (C.I. 21090)
Product Code	S6152/OPQ
CAS NO.	6358-85-6
EC No.	228-787-8
Chemical Formula	$C_{32}H_{26}CI_2N_6O_4$

Physical Properties

Density (g/cm³)	1.35-1.55
Specific Surface Area(m ² /g)	30-70
Oil Absorption (g/100g)	20-65
PH Value	5.0-8.5
Bulk Density (lb/gal)	9.0-13.0
Total impurities(ppm)	≦600

Fastness Properties

Heat Resistance (°C)	160	Alkali Resistance
Light Resistance (Full Shade, 1-8)	2-3	Migration Resist
Light (Reduced tinting, 1-8)	1-2	Ethyl Acetate (1
Weather Resistance (1-5)	4	Ethanol (1-5)
Acid Resistance (1-5)	4	MEK (1-5)

Alkali Resistance (1-5)	4
Migration Resistance(1-5)	3
Ethyl Acetate (1-5)	3
Ethanol (1-5)	4
MEK (1-5)	2

Application & Performance

Recommended for solvent-based application, it is Opaque standard with high color strength and good viscosity, mostly for solvent-based Ink.

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue Sep 1st , 2024

TDS Version 2.1