Technical Data Sheet



Pigment Yellow 12

General Information

| Color Index | Pigment Yellow 12 (C.I. 21090) |
|------------------|--------------------------------|
| Product Code | W6112 |
| CAS NO. | 6358-85-6 |
| EC No. | 228-787-8 |
| Chemical Formula | $C_{32}H_{26}CI_2N_6O_4$ |

Physical Properties

| Density (g/cm³) | 1.35-1.55 |
|--|-----------|
| Specific Surface Area(m ² /g) | 40-75 |
| Oil Absorption (g/100g) | 28-78 |
| PH Value | 5.0-8.5 |
| Bulk Density (lb/gal) | 9.3-13.6 |
| Total impurities(ppm) | ≦600 |

Fastness Properties

| Heat Resistance (°C) | 160 |
|------------------------------------|-----|
| Light Resistance (Full Shade, 1-8) | 2-3 |
| Light (Reduced tinting, 1-8) | 1-2 |
| Weather Resistance (1-5) | 4 |
| Acid Resistance (1-5) | 4 |

| Alkali Resistance (1-5) | 4 |
|---------------------------|---|
| Migration Resistance(1-5) | 3 |
| Ethyl Acetate (1-5) | 3 |
| Ethanol (1-5) | 4 |
| MEK (1-5) | 2 |

Application & Performance

Recommended for textile printing, good color strength and dispersions.

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

> Date of issue Sep 1st, 2024 TDS Version 2.1

Hangzhou Fancheng Chemical Co.,Ltd.

Add NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China.

Tel +86-571-83531793